

Silikon za ogledala

Opis proizvoda

Silikonski zaptivač za ogledalo je jednodelni silikonski zaptivač na bazi alkoksi, neutralnog očvršćavanja.

Svojstva

- Neutralan lek
- Nizak modul, visoka elastičnost
- Dobra adhezija bez prajmera na različite podloge
- Nije korozivan za metale
- Jednostavan za nanošenje i alat
- Slab miris
- U skladu sa ISO 11600 – F&G – 25 ML
- Otporan na ozon, ultraljubičasto zračenje i ekstremne temperature
- Sadrži fungicid

Tehnički podaci

Hemijska baza: Alkoki silikon, neutralno očvršćavanje

Specifična težina: $1,01 \pm 0,03 \text{ gr/cm}^3$

(ASTM D 1045-86)

Ekstruzija: 140–220 g/min

(ISO 6927)

Vreme bez lepljenja: 45–50 min.

(25°C i 50% R.H)

Stopa očvršćavanja (1 dan): 1,8 mm

(25°C i 50% R.H)

Modul na 100% (MPa): 0, 23 MPa

(ASTM D412)

Zatezna čvrstoća: > 1 MPa

(ASTM D412)

Izduženje pri prekidu: % 500

(ASTM D412)

Tvrdoća po Šoru: 10 Shore A

(ASTM D 53505)

Otpornost na temperaturu: mak. 180 °C

Detalji o primeni

Temperatura primene: +5 °C do 40 °C

Površina za nanošenje mora biti čvrsta, čista suva i očišćena od prašine, ulja i masti.

Koristi se za zastakljivanje i zaptivanje svih vrsta prozora (PVC, drvo, aluminijum)

Adhezija na većinu poroznih i neporoznih podloga uključujući;

- Zidanje
- Cigla
- Aluminijum
- Metali
- PVC
- Poliakrilat
- Polikarbonat
- Impregnirano, lakirano ili farbano drvo
- Staklene površine
- Površine za zastakljivanje

Pakovanje

U kertridžu od 310 ml

Boja

Crvena, plava, crna, bela, providna

Rok trajanja

Čuvajte proizvod na hladnom i suvom mestu. Rok upotrebe je 12 meseci.

Temperatura skladištenja: minimalno -10°C, maksimalno +32°C



šifra: SOG

barkod: 8606007997507

Mirror silicone

Product Description

Mirror silicone sealant is one part neutral curing, gunnable, alkoxy based silicone sealant.

Properties

- Neutral cure
- Low modulus, high elasticity
- Good unprimed adhesion to a variety of substrates
- Non corrosive to metals
- Easy to apply and tool
- Low odor
- Conforms to ISO 11600 – F&G – 25 ML
- Resistant to ozone, ultra-violet radiation and temperature extreme
- Contains fungicide

Technical Information

Chemical Base: Alkoxy silicone, neutral curing

Specific gravity: $1,01 \pm 0,03 \text{ gr/cm}^3$

(ASTM D 1045-86)

Extrusion: 140–220 g/min

(ISO 6927)

Tack free time: 45–50 min.

(25°C and 50% R.H)

Cure Rate(1 day): 1,8 mm

(25°C and 50% R.H)

Modulus at 100% (MPa): 0, 23 MPa

(ASTM D412)

Tensile Strength: > 1 MPa

(ASTM D412)

Elongation at Break: % 500

(ASTM D412)

Shore Hardness: 10 Shore A

(ASTM D 53505)

Temperature Resistance: max. 180 °C

Application Details

Application Temperature: +5 °C to 40 °C

The application surface must be solid, clean dry and free of dust, oil and grease.

It is used for glazing and weathersealing of all types of windows (PVC, wood, aluminum)

Adhesion to most porous and non-porous substrates including;

- Masonry
- Brick
- Aluminum
- Metals
- PVC
- Polyacrylate
- Polycarbonate
- Impregnated, varnished or painted wood
- Glass surfaces
- Glazing surfaces

Packaging

In 310 ml cartridge

Color

Red, Blue, Black, White, Transparent

Shelf Life

Store the product in a cool and dry place. The shelf life is 12 months.

Storage temperature: minimum -10°C, maximum +32°C



code: SOG
barcode: 8606007997507